

# ORIABAG PAPER

FLEXO / OFFSET \_ FLEXO / OFFSET \_ FLEXO / OFFSET

OCR \_ OCR \_ OCR

CARACTERÍSTICAS CHARACTERISTICS CARACTERISTIQUES	[V]	Especificación y tolerancia Specification and tolerance Spécification et tolérance	Norma de ensayo Standard test Norme d'essai	GRAMAJE / SUBSTANCE / GRAMMAGE													
GRAMAJE SUBSTANCE GRAMMAGE	g/m <sup>2</sup>	± 4% (resto) ± 3% (100<g<224)	ISO 536	50	60	70	80	90	100	110	120	140	160	200	250		
MANO BULK MAIN	cm <sup>3</sup> /g	± 0,05	ISO 534			1,15	1,15	1,10	1,10	1,10	1,10	1,05	1,05				
HUMEDAD ABSOLUTA ABSOLUTE HUMIDITY HUMIDITÉ ABSOLUE	%	± 1	ISO 287			5	5	5	5	5	5	5	5				
ENCOLADO COBB 60 COBB 60 INDEX COLLAGE COBB 60	g/m <sup>2</sup>	-	ISO 535			≤28	≤28	≤28	≤28	≤28	≤28	≤28	≤28				
POROSIDAD BENDTSEN BENDSTEN POROSITY POROSITÉ BENDSTEN	ml/min	-	UNE 57066-2			<1000	<1000	<1000	<1000	<1000	<1000	<1000	<1000				
BLANCURA* WHITENESS* BLANCHEUR*	CIE	± 5	ISO 2470-1			-	-	-	-	-	-	-	-				
OPACIDAD OPACITY OPACITÉ	%	± 2	UNE 57063			84	86	88	90	92	92	93	94				
LISURA BENDSTEN cara tela / cara fieltro SMOOTHNESS BENDSTEN wire side / top side LISSÉ BENDSTEN côte toile / côte feutre	ml/min	± 50	UNE 57080-2			140/100	140/100	140/100	140/100	140/100	160/120	160/120	160/120				
LONGITUD ROTURA Long. BREAKING LENGTH Long. LONGEUR DE RUPTURE Long.	m	-	UNE 1924-2			>7000	>7000	>6500	>6500	>6500	>6000	>6000	>6000				
LONGITUD ROTURA Trans. BREAKING LENGTH Trans. LONGEUR DE RUPTURE Trans.	m	-	UNE 1924-2			>4500	>4500	>4500	>4500	>4500	>4000	>4000	>4000				
INDICE DESGARRO Long. / Transv. RATE OF TEAR Long. / Transv. INDICE DÉCHIRURE Long. / Transv.	g	± 15	ISO 1974			70/80	70/80	70/80	70/80	70/80	70/80	80/90	80/90				

OBSERVACIONES OBSERVATIONS OBSERVATIONS

BLANCURA WHITENESS BLANCHEUR

Medición realizada con espectrofotómetro Frank-PTI Measurement made in spectrophotometer Frank-PTI Mesure faite au spectrophotometre Frank-PTI

PASTAS EMPLEADAS PULPS USED PÂTES EMPLOYÉES

Pastas químicas ECF Chemical pulps ECF Pâtes chimiques ECF



CONTACTO CONTACT CONTACT

ERNIO BIDEA, 8 BIS

ZIZURKIL (ESPAÑA)

TEL: 0034-943690200

FAX: 0034943691550

[www.papeleradeloria.es](http://www.papeleradeloria.es)